



Testing Laboratory
0292

Material and Engineering Laboratory-Taichung

TEST REPORT



REPORT NO. TV-19-03156A
PAGE NO. 1 OF 1
DATE: Aug. 29, 2019

KWO LIN CO., LTD.

NO. 25, Jhengguang St., Taiping Dist., Taichung City 411, Taiwan

Product Name High Durable Powder Coating
Product Type DP
Product Submitted By KWO LIN CO., LTD.
Date of Sample Received Aug. 23, 2019
Date of Testing Aug. 23, 2019~Aug. 29, 2019
Remark 1. The information mentioned in the above section is provided by Client
(Exclude Date of Sample Received and Date of Testing)
2. The following report content marks # is provided by Client.


Test Result :

| Test Item | Test Method | Result |
|--|-----------------|-----------|
| Resistance to Acid(5% H_2SO_4 , Room temp. , 24hr.) | CNS 10757(1995) | No Effect |
| Resistance to Alkali(5% Na_2CO_3 , Room temp. , 24hr.) | CNS 10757(1995) | No Effect |

Note : This Test Report is an additional original report of TV-19-03156. Issued date : Aug. 29, 2019.

--oOo--

The required specification(s) offered in this test report is/are for reference only
The conformity judgment is at the Applicant's final verdict.


Signed for and on behalf of
SGS Taiwan Ltd.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司

No. 9, 14th Rd. Taichung Industrial Park, Taichung 40755, Taiwan / 40755 台中市台中工業區14路9號
t (886-4) 2359-1515

f (886-4) 2359-2557

www.sgs.com.tw

Member of SGS Group

TWC 7550639

no0n_chou